

The application was originally made under the Patent Cooperation Treaty with the German Patent Office acting as the receiving office on (86) 23 Oct 1980, being given an application number PCT/DE80/00153. The application was searched by the European Patent Office acting as the International Search Authority (ISA), and published by the International Bureau on (87) 28 May 1981 under serial number WO 81/01375 in the German language. The text of the application is contained in the publication made by the International Bureau as above identified, the accompanying text being an English translation thereof.


(12) UK Patent Application (19) GB (11) 2 075 368 A

- (21) Application No 8122404
 (22) Date of filing 23 Oct 1980
 (30) Priority data
 (31) 2947025
 (32) 22 Nov 1979
 (33) Fed Rep of Germany (DE)
 (43) Date of issue
 18 Nov 1981
 (51) INT CL³ (as given by ISA)
 B05D 5/08
 F16C 33/20
 (52) Domestic classification
 B2E 440T 516T 603T KB
 (56) Documents cited by ISA
 DE A 2206400
 DE A 2033067
 DE A 2366046
 GB A 1564128
 DE A 2305696
 DE A 2818184
 FRA 2307034
 DE A 2000632
 (58) Field of search by ISA
 INT CL³ F16C 33/20; B05
 D7/16; 7/00, 5/08

- (71) Applicants
 Glyco Metall Werke
 Daelen & Loos GMBH
 Stielstrasse 11,
 6200 Wiesbaden N. W.
 Germany
 (72) Inventors
 Danilo Sternisa
 Erich Hodas
 Walter Schneider
 (74) Agents
 Withers & Rogers
 4, Dyer's Buildings
 Holborn
 London EC1N 2JT

(54) Composite material with two or a plurality of layers

(57) Composite material with two or a plurality of layers with a coating layer (5) which is applied directly on the rough surface (2) of a substrate and which comprises a lake base of polyimide and at least one finely spread additive in said base. Upon forming the coating layer (5) as a friction or sliding layer, such layer may contain about 99 to 60% by volume, preferably 90 to 80% by volume of thermo-setting polyimide lake and about 1 to 40% by volume, preferably 10 to 20% by volume of self-lubrication additives, particularly low molecular weight PTFE, with a grain size comprised between 5 and 7 μm . For manufacturing said composite material, the powder additive is intimately mixed with the polyimide lake and homogenized until it becomes slightly viscous or pasty, deposited on the metal substrate and fixed thereto by sintering.



GB 2 075 368 A